





Technical Data Sheet

Product Name	3,4-Epoxy cyclohexylmethyl 3,4-epoxycyclohexane carboxylate
Synonyms	7-Oxabicyclo[4.1.0]hept-3-ylmethyl 7-oxabicyclo[4.1.0]heptane-3-carboxylate
CAS No	2386-87-0
Molecular Structure	
Country of Origin	China
Description	<p>Brand Name: TTA21 (JR-HS-21, UVR6110, ERL4221) Appearance: Pale Yellow to Colorless Transparent Liquid Weight per Epoxide: 131~143 Color: 100APHA max Viscosity @ 25 deg.C: 350~450 cP Package: 200kg Net Iron Drum Application: TTA21 is miscible with a wide range of organic solvents, including acetone, ethanol, and benzene. It's low viscosity and good fluidity makes it suitable for use in bulk manufacturing. The long term stability at ambient temperature is very good. It will react in the presence of acid anhydride curing agents at higher temperature. With above 200°C Martin heat resistance, the cured product is suitable for use at high temperatures between 200-250°C for long periods.</p>
Pictures	

海南 Hainan

地址: 海口市文华路18号文华大酒店8层811室
Add: Room 811, Hainan Mandarin Hotel, No.18, Wenhua Road,
Haikou, Hainan, China.
邮编 PC: 570105
电话 TEL: 0086-898-36625599 传真 FAX: 0086-898-68540119
邮箱 Email: sales@zxchem.com.cn

上海 Shanghai

地址: 上海市桂平路418号兴园科技广场26楼
Add: Rm 1206, Mingshen Business Plaza, 400 Caobao Road,
Shanghai, P.R.China.
邮编 PC: 200233
电话 TEL: 0086-021-54265599 传真 FAX: 0086-021-64821580
邮箱 Email: sales@zxchem.com.cn