





Technical Data Sheet

Product Name	2-Mercaptobenzothiazole	
Synonyms	Refined MBT	
CAS No	149-30-4	
Molecular Structure		
Specification	Appearance (visual inspection) Light yellow powder (Granule) Initial M.P. °C ≥ 172.0 heating loss % ≤ 0.40 Ash% ≤ 0.40 Residues on sieve(150μm), % ≤ 0.10 Residues on sieve(63μm), % ≤ 0.50	
Application	MBT is fast and nonpolluting accelerator suitable for rubbers and latex; can achieve good cold vulcanization when used together with secondary accelerator TMTD, TETD, DPG; it gives vulcanized rubbers excellent anti-aging property, and is mainly used in the manufacture of tyre, adhesive tape, rubber overshoes and other rubber products; can not be used as food material.	
Hazard Class	UN 3077 9/Pg 3	
Packing	25kg plastic woven bag, paper with plastic film bag, kraft paper bag or jumbo bag	
Quantity /20'FCL	17MTS without pallets	

海南 Hainan

地址: 海口市文华路18号文华大酒店8层811室
Add: Room 811, Hainan Mandarin Hotel, No. 18, Wenhua Road, Haikou, Hainan, China.
邮编 PC: 570105
电话 TEL: 0086-898-36625599 传真 FAX: 0086-898-68540119
邮箱 Email: sales@zxchem.com.cn

上海 Shanghai

地址: 上海市桂平路418号兴园科技广场26楼
Add: Rm 1206, Mingshen Business Plaza, 400 Caobao Road, Shanghai, P.R.China.
邮编 PC: 200233
电话 TEL: 0086-021-54265599 传真 FAX: 0086-021-64821580
邮箱 Email: sales@zxchem.com.cn