




## Technical Data Sheet

<b>Product Name</b>	Electrolytic Manganese Metal Flakes	
<b>Model Number</b>	99.7%,99.85%,99.9%	
<b>Shape</b>	Flakes	
<b>Specification</b>	<p>Grade 99.7 Mn:99.70%min C:0.040%max S:0.050%max P:0.005%max Fe+Si+Se:0.205%max</p> <p>Grade 99.85 Mn:99.85%min C:0.023%max S:0.030%max P:0.005%max Fe+Si+Se:0.1%max</p> <p>Grade 99.9 Mn:99.90%min C:0.010%max S:0.018%max P:0.003%max Fe+Si+Se:0.073%max</p>	
<b>Application</b>	Used in the high performance soft magnetization ferrite, high magnetic permeability ferrite, high saturated magnetic induction density low cost ferrite; High stable low cost ferrite.	
<b>Size</b>	100% below 55mm all dimensions Average Thickness 0.8~1.20mm min	
<b>Packing</b>	In 1 MT Plastic woven bags or according the buyer requirement	
<b>Delivery detail</b>	Within 20 days after the receipt of L/C or advance payment	
<b>Quantity /20'FCL</b>	23-25 MTS	

### 海南 Hainan

地址: 海口市滨海大道201号黄金海岸花园66幢1层  
Add: 66 Building, Gold Coast Garden, Binhai Avenue 201,  
Haikou, Hainan, China  
邮编 PC: 570312  
电话 TEL: 0086-898-68540310 传真 FAX: 0086-898-68540119  
邮箱E-mail: sales@zxchem.com.cn

### 上海 Shanghai

地址: 上海市桂平路418号兴园科技广场26楼260A室  
Add: Room260A, 26F, Xingyuan Technology Building,  
No. 418, Guiping Road, Shanghai, China  
邮编 PC: 200233  
电话 TEL: 0086-21-54265599 传真 FAX: 0086-21-64821580  
邮箱E-mail: sales@zxchem.com.cn