




Technical Data Sheet

Product Name	Ferro Manganese	
Model Number	HC/MC/LC	
Shape	Lumps	
Specification	<p>High Carbon Ferro Manganese Mn: 75%min Si: 1.5%max C: 7%max P: 0.4%max S: 0.05%max</p> <p>Middle Carbon Ferro Manganese Mn: 75%-80%min Si: 1-1.5%max C: 1.5-2.0%max P: 0.4%max S: 0.05%max</p> <p>Low Carbon Ferro Manganese Mn: 75%-80%min Si: 1-1.5%max C: 0.5-1.0%max P: 0.4%max S: 0.05%max</p>	
Application	<p>1. Ferro Manganese is an alloy of Iron and manganese, with manganese between 65.0%~90.0%, as deoxidizer and alloying element additive. Divided into furnace ferromanganese and blast furnace ferromanganese.</p> <p>2. Main categories: high carbon ferromanganese (carbon 7%), medium carbon ferromanganese (carbon 1.0~1.5%), low carbon ferromanganese (0.5% carbon), metal manganese, Spiegel, Silicon-manganese alloy.</p> <p>3. International general standard for carbon ferromanganese containing manganese with 75 ~ 80%. To adapt to the conditions of low grade raw ore, China provides manganese lower grades</p>	
Size	10-50mm 10-100mm 50-100mm	
Packing	In 1 MT bulk big bag or according the buyer requirement	
Delivery detail	Within 20 days after the receipt of L/C or advance payment	
Quantity /20'FCL	23-25 MTS	

海南 Hainan

地址: 海口市滨海大道201号黄金海岸花园66幢1层
Add: 66 Building, Gold Coast Garden, Binhai Avenue 201,
Haikou, Hainan, China
邮编 PC: 570312
电话 TEL: 0086-898-68540310 传真 FAX: 0086-898-68540119
邮箱E-mail: sales@zxchem.com.cn

上海 Shanghai

地址: 上海市桂平路418号兴园科技广场26楼260A室
Add: Room260A, 26F, Xingyuan Technology Building,
No. 418, Guiping Road, Shanghai, China
邮编 PC: 200233
电话 TEL: 0086-21-54265599 传真 FAX: 0086-21-64821580
邮箱E-mail: sales@zxchem.com.cn